

No : **KDI-L 3111**
REPORT OF ANALYSIS

Principal : **PT. GARDA PRIMA ENERGI**
 Subject : Drop Off Sample Analysis
 Parameter of Analysis : Mineral Analysis
 Description of Sample : Nickel Ore : 33 sample (s)
 Packing : Unsealed Plastic Bags
 Reference : QUO/TRIBHAKTI/23/VI/2170
 Date of Sample Received : July 14, 2023
 Date of Analysis : July 16, 2023
 SO Number : SO-34484
 Number of Page : 1 Page

THIS IS TO REPORT that upon the request of the principal, the sample received was analyzed at Laboratory of PT TRIBHAKTI INSPEKTAMA in accordance with XRF Press Pellet method. The results are as stated below :

No.	Sample ID	Weight (Kg)	Ni	Fe	Co	Na2O	MgO	Al2O3	SiO2	P2O5	SO3	K2O	CaO	TiO2	Cr2O3	MnO	MC
			%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
1	DOME 1 GPE	2.92	1.62	12.10	0.07	0.01	25.28	1.75	40.80	<0.01	<0.01	<0.01	0.54	0.04	0.81	0.23	38.18
2	DOME 2 GPE	2.19	1.69	11.75	0.06	<0.01	23.82	1.86	41.16	<0.01	<0.01	<0.01	0.58	0.05	0.91	0.22	35.66
3	DOME 3 GPE	3.40	1.59	11.79	0.07	<0.01	28.81	1.12	38.90	<0.01	<0.01	<0.01	0.13	0.02	0.58	0.23	44.32
4	DOME 4 GPE	3.51	1.42	12.65	0.07	<0.01	25.11	1.39	40.29	<0.01	<0.01	<0.01	0.18	0.03	0.95	0.27	38.47
5	DOME 5 GPE	2.69	1.57	15.61	0.07	<0.01	22.79	1.05	38.55	<0.01	<0.01	<0.01	0.10	0.02	0.87	0.31	45.54
6	DOME 6 GPE	3.49	1.59	16.08	0.07	<0.01	21.98	2.15	38.07	<0.01	<0.01	<0.01	0.23	0.04	1.11	0.35	40.48
7	DOME 7 GPE	3.33	1.73	18.94	0.08	0.01	22.69	1.72	33.11	<0.01	<0.01	<0.01	0.09	0.04	0.88	0.43	38.91
8	DOME 8 GPE	2.04	1.66	18.72	0.08	0.01	21.59	2.05	33.72	<0.01	<0.01	<0.01	0.20	0.05	0.84	0.43	38.79
9	DOME 9 GPE	3.72	1.43	13.36	0.07	0.02	26.64	1.79	37.01	<0.01	<0.01	<0.01	0.45	0.04	0.94	0.29	33.55
10	DOME 10 GPE	3.82	1.46	14.61	0.07	0.02	23.55	2.35	37.72	<0.01	<0.01	<0.01	0.87	0.06	0.93	0.32	37.53
11	DOME 11 GPE	3.82	1.56	13.97	0.07	0.02	25.38	2.26	37.98	<0.01	<0.01	<0.01	0.69	0.05	0.89	0.30	36.47
12	DOME 12 GPE	3.51	1.47	16.58	0.08	0.01	22.41	2.84	35.63	<0.01	<0.01	<0.01	0.58	0.07	1.11	0.37	32.78
13	DOME 13 GPE	3.53	1.59	18.59	0.08	0.02	17.23	3.89	36.34	<0.01	<0.01	<0.01	0.24	0.10	1.17	0.43	43.80
14	DOME 14 GPE	4.02	1.55	18.92	0.08	0.02	15.51	5.41	36.61	<0.01	<0.01	<0.01	0.55	0.15	1.27	0.41	45.14
15	DOME 15 GPE	2.22	1.90	20.20	0.08	0.02	15.90	4.09	34.23	<0.01	<0.01	<0.01	0.37	0.15	1.48	0.43	44.56
16	DOME 16 GPE	1.75	1.39	16.27	0.07	0.01	17.66	6.40	36.80	<0.01	<0.01	<0.01	0.68	0.13	1.14	0.37	31.52
17	DOME 17 GPE	3.27	1.61	22.27	0.07	0.01	14.74	4.86	32.31	<0.01	<0.01	<0.01	0.33	0.11	1.36	0.47	40.07
18	DOME 18 GPE	3.45	1.59	21.71	0.08	0.01	12.93	5.42	33.72	<0.01	<0.01	<0.01	0.27	0.16	1.30	0.46	46.29
19	DOME 19 GPE	2.69	1.76	21.26	0.08	0.01	16.73	4.06	33.22	<0.01	<0.01	<0.01	0.16	0.10	1.21	0.44	43.59
20	DOME 20 GPE	2.96	1.47	15.82	0.07	0.02	23.76	1.87	36.74	<0.01	<0.01	<0.01	0.17	0.04	0.81	0.33	38.34
21	DOME 21 GPE	2.05	1.61	18.63	0.08	0.01	16.93	4.15	36.14	<0.01	<0.01	<0.01	0.50	0.11	1.09	0.40	42.94
22	DOME 22 GPE	2.17	1.72	23.82	0.08	0.02	14.93	4.16	30.11	<0.01	<0.01	<0.01	0.25	0.10	1.24	0.50	44.64
23	DOME 23 GPE	2.44	1.98	18.10	0.07	0.01	23.28	1.40	33.80	<0.01	<0.01	<0.01	0.10	0.04	0.91	0.36	40.65
24	DOME 24 GPE	2.45	1.79	23.34	0.08	0.02	12.52	5.51	31.58	<0.01	<0.01	<0.01	0.29	0.13	1.54	0.52	45.81
25	DOME 25 GPE	3.58	1.71	29.39	0.06	0.01	12.41	3.13	25.39	<0.01	<0.01	<0.01	0.12	0.08	1.85	0.64	43.86
26	DOME 26 GPE	4.15	1.47	20.21	0.08	0.02	12.06	7.56	34.78	<0.01	<0.01	<0.01	0.61	0.16	1.44	0.49	42.96
27	DOME 27 GPE	2.44	1.66	24.86	0.08	0.02	9.50	7.24	31.04	<0.01	<0.01	<0.01	0.24	0.17	1.56	0.55	44.80
28	DOME 28 GPE	4.15	1.37	16.40	0.07	<0.01	23.21	1.32	37.23	<0.01	<0.01	<0.01	0.02	0.03	0.73	0.34	36.68
29	DOME 29 GPE	3.65	1.69	21.43	0.08	0.02	20.25	1.63	31.07	<0.01	<0.01	<0.01	0.02	0.04	1.03	0.44	43.62
30	DOME 30 GPE	4.66	1.81	19.50	0.08	0.01	19.48	2.45	33.03	<0.01	<0.01	<0.01	0.26	0.06	0.98	0.39	41.09
31	DOME 31 GPE	4.45	1.77	21.91	0.07	0.01	14.68	5.11	32.46	<0.01	<0.01	<0.01	0.31	0.12	1.33	0.46	41.16
32	DOME 32 GPE	4.89	1.57	20.65	0.06	0.02	11.04	7.72	34.48	<0.01	<0.01	<0.01	0.55	0.16	1.51	0.48	35.35
33	DOME 33 GPE	4.45	1.54	25.49	0.06	0.02	7.24	9.27	30.24	<0.01	<0.01	<0.01	0.35	0.21	1.63	0.55	43.63

This report is prepared and issued by the Company upon request by Principal/Applicant and the analysis contain therein reflects the Company's findings on the analysis of sample submitted by the Principal/Applicant and/or drawn by the Company at the time and place of performing the inspection/testing only. The Company shall not be liable to any legal consequences resulting from any business or transaction using this report.

KENDARI, JULY 17, 2023

Signed on behalf of

PT TRIBHAKTI INSPEKTAMA


 L-16

 Asrani Purwanti
 Laboratory Manager

Cert No : MNR-2302KDI.521

Branch Office Kendari :

 Jl. Brigjen Katamso, Baruga Kendari - Sulawesi Tenggara
 Phone : +62 0401-3094-755

Branch Offices :

 JAKARTA, SAMARINDA, BERAU, BULUNGAN, BANJARMASIN, BATULICIN, MUARA TEWEH, ACEH,
 MEDAN, BATAM, PADANG, JAMBI, BENGKULU, LAMPUNG, PALEMBANG, KENDARI
