

No: **KDI-L 3012**
REPORT OF ANALYSIS


Principal : **PT. GARDA PRIMA ENERGIE**
 Subject : Drop Off Sample Analysis
 Parameter of Analysis : Mineral Analysis
 Description of Sample : Nickel Ore : 14 sample (s)
 Packing : Unsealed Plastic Bags
 Reference : QUO/TRIBHAKTI/23/VI/2170
 Date of Sample Received : June 25, 2023
 Date of Analysis : June 26, 2023
 SO Number : SO-33759
 Number of Page : 1 Page

THIS IS TO REPORT that upon the request of the principal, the sample received was analyzed at Laboratory of PT TRIBHAKTI INSPEKTAMA in accordance with XRF Press Pellet method. The results are as stated below :

No.	Sample ID	Weight (Kg)	NI	Fe	Co	Na2O	MgO	Al2O3	SiO2	P2O5	SO3	K2O	CaO	TiO2	Cr2O3	MnO	MC
			%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
1	DOME 01	4.95	1.64	22.86	0.05	0.06	8.96	8.42	32.80	<0.01	<0.01	<0.01	0.73	0.28	1.69	0.49	44.79
2	DOME 02	4.51	1.73	18.41	0.04	0.05	10.91	6.98	39.04	<0.01	<0.01	<0.01	0.98	0.21	1.43	0.43	40.07
3	DOME 03	5.21	1.67	15.85	0.03	0.07	14.51	5.66	40.11	<0.01	<0.01	<0.01	0.97	0.19	1.09	0.30	31.47
4	DOME 04	3.50	1.67	17.60	0.03	0.06	13.61	5.96	38.53	<0.01	<0.01	<0.01	0.83	0.19	1.19	0.37	42.51
5	DOME 05	5.47	1.51	18.67	0.04	0.05	12.02	7.11	37.56	<0.01	<0.01	<0.01	1.35	0.23	1.34	0.41	38.80
6	DOME 06	4.52	1.52	16.43	0.03	0.06	13.22	7.44	38.77	<0.01	<0.01	<0.01	1.50	0.23	1.26	0.37	37.31
7	DOME 07	4.28	1.57	16.92	0.04	0.06	13.30	6.83	38.61	<0.01	<0.01	<0.01	1.09	0.20	1.25	0.39	39.13
8	DOME 08	4.78	1.50	19.64	0.04	0.06	10.63	7.97	35.71	<0.01	<0.01	<0.01	1.05	0.24	1.53	0.48	42.93
9	DOME 09	5.36	1.58	24.36	0.05	0.04	7.28	9.65	31.22	<0.01	<0.01	<0.01	0.74	0.30	1.81	0.59	44.58
10	DOME 10	6.60	1.63	20.76	0.04	0.06	9.27	8.36	34.51	<0.01	<0.01	<0.01	0.80	0.27	1.43	0.45	42.45
11	DOME 11	5.14	1.46	28.53	0.06	0.05	6.52	9.95	25.38	<0.01	<0.01	<0.01	0.38	0.29	1.96	0.69	41.16
12	DOME 12	3.06	1.71	19.54	0.04	0.06	10.26	8.38	36.35	<0.01	<0.01	<0.01	1.17	0.29	1.56	0.41	37.67
13	DOME 13	5.58	1.73	21.06	0.05	0.05	15.70	3.96	34.56	<0.01	<0.01	<0.01	0.62	0.12	1.48	0.46	40.96
14	DOME 14	3.39	1.87	18.72	0.04	0.05	13.14	6.67	36.40	<0.01	<0.01	<0.01	0.58	0.21	1.38	0.46	41.27

This report is prepared and issued by the Company upon request by Principal/Applicant and the analysis contain therein reflects the Company's findings on the analysis of sample submitted by the Principal/Applicant and/or drawn by the Company at the time and place of performing the inspection/testing only. The Company shall not be liable to any legal consequences resulting from any business or transaction using this report.

KENDARI, JUNE 27, 2023

 Signed on behalf of
PT TRIBHAKTI INSPEKTAMA

Asrani Purwanti
 Laboratory Manager

Cert No : MNR-2302KDI.471
Branch Office Kendari :

 Jl. Brigjen Katamsa, Baruga Kendari - Sulawesi Tenggara
 Phone : +62 0401-3094-755

Branch Offices :

 JAKARTA, SAMARINDA, BERAU, BULUNGAN, BANJARMASIN, BATULICIN, MUARA TEWEH, ACEH,
 MEDAN, BATAM, PADANG, JAMBI, BENGKULU, LAMPUNG, PALEMBANG, KENDARI
